

10070244-060602

JG18 Rec'd PCT/PTO 04 MAR 2002

FORM PTO-1390		U.S. Department of Commerce Patent and Trademark Office	Attorney's Docket No. 1604-130
<b>TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371</b>			U.S. Application No. (if known, see 37 CFR 1.5) <b>10/070244</b>
INTERNATIONAL APPLICATION NO. PCT/ES00/00335	INTERNATIONAL FILING DATE September 1, 2000	PRIORITY DATE CLAIMED September 3, 1999	
<b>TITLE OF INVENTION</b> NEW BIOCOMPATIBLE POLYMER SYSTEMS CARRYING TRIFLUSAL OR HTB			
<b>APPLICANT(S) FOR DO/EO/US</b> Alberto Gallardo Ruiz, Gema Rodriguez Crespo, Julio San Roman Del Barrio			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<ol style="list-style-type: none"><li>1. <input checked="" type="checkbox"/> This is a <b>FIRST</b> submission of items concerning a filing under <u>35 U.S.C. 371</u></li><li>2. <input type="checkbox"/> This is a <b>SECOND</b> or <b>SUBSEQUENT</b> submission of items concerning a filing under 35 U.S.C. 371.</li><li>3. <input type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.</li><li>4. <input type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31).</li><li>5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2))<ol style="list-style-type: none"><li>a. <input type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau).</li><li>b. <input checked="" type="checkbox"/> has been communicated by the International Bureau.</li><li>c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US)</li></ol></li><li>6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).<ol style="list-style-type: none"><li>a. <input checked="" type="checkbox"/> is attached hereto.</li><li>b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4)</li></ol></li><li>7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))<ol style="list-style-type: none"><li>a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau).</li><li>b. <input type="checkbox"/> have been communicated by the International Bureau.</li><li>c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</li><li>d. <input checked="" type="checkbox"/> have not been made and will not be made.</li></ol></li><li>8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</li><li>9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</li><li>10. <input type="checkbox"/> An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).</li></ol>			
<b>ITEMS 11. TO 20. below concern other document(s) or information included:</b>			
<ol style="list-style-type: none"><li>11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</li><li>12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</li><li>13. <input checked="" type="checkbox"/> A <b>FIRST</b> preliminary amendment.</li><li>14. <input type="checkbox"/> A <b>SECOND</b> or <b>SUBSEQUENT</b> preliminary amendment</li><li>15. <input type="checkbox"/> A substitute specification.</li><li>16. <input type="checkbox"/> A change of power of attorney and/or address letter.</li><li>17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825</li><li>18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4).</li><li>19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).</li><li>20. <input checked="" type="checkbox"/> Other items or information: - Copy of WO 01/17578 with Search Report</li></ol>			

Barbara G. Ernst  
Rothwell, Figg, Ernst & Manbeck  
555 13th St., N W  
Washington, D.C 20004  
Phone: 202/783-6040

1604-130

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of )  
 )  
Alberto Gallardo Ruiz et al. ) Filing Under 35 USC 371  
 ) International Application  
Serial No. ) No. PCT/ES00/00335  
 ) Filed September 1, 2000  
Filed: )  
 )  
For: NEW BIOCOMPATIBLE POLYMER)  
 )  
SYSTEMS CARRYING )  
 )  
TRIFLUSAL OR HTB )

PRELIMINARY AMENDMENT


Assistant Commissioner for Patents  
Washington, D.C. 20231

Dear Sir:

Prior to examination of the above-referenced patent  
application, please cancel claims 1-36 and add the following  
claims:

## New Claims

37.- A polymeric compound of relative general formula I



(I)

wherein:

A represents a residue of a polymerisable acrylic or vinylic monomer carrying triflusal or HTB, wherein triflusal or HTB are linked to the remainder of the monomer molecule through an *in vivo* hydrolysable covalent bond;

B represents a residue of a second polymerisable monomer;

m and n represent the molar fractions of the monomers A and B in the polymer so that m + n is always 1 and m is always different from 0;


and wherein the A and B units are distributed randomly in the polymer.

38.- A compound according to claim 37 wherein the hydrolysable covalent bond through which triflusal or HTB are linked is a carboxylic ester bond.

39.- A compound according to claim 37 wherein n represents 0.

40.- A compound according to claim 37 wherein n is different from 0.

41.- A compound according to claim 37 of relative formula **Ia**:



(Ia)

wherein:  $\text{R}_1$  represents hydrogen or  $\text{C}_{1-4}$  alkyl;  
 $\text{R}_2$  represents  $-\text{COCH}_3$  or hydrogen;  
 $\text{X}$  represents  $-(\text{CH}_2\text{CH}_2\text{O})_p$ ;  
 $p$  represents an integer from 1 to 100; and  
 $\text{B}$ ,  $m$  and  $n$  have the meaning described in claim 1.

42.- A compound according to claim 41 wherein  $\text{R}_1$  represents methyl and  $p$  represents 1.

43.- A compound according to claim 42 wherein  $n$  represents 0.

44.- A compound according to claim 42 wherein  $n$  is different from 0.

45.- A compound according to claim 44 wherein  $\text{B}$  represents a residue of 2-hydroxyethyl methacrylate, methyl methacrylate, methyl acrylate, N-vinylpyrrolidone, acrylic acid, methacrylic acid, acrylamide, N,N-dimethylacrylamide, vinyl acetate or 2-acrylamido-2-methylpropanesulfonic acid.

46.- A compound according to claim 45 wherein  $\text{B}$  represents a residue of N,N-dimethylacrylamide.

47.- A compound according to claim 45 wherein B represents a residue of 2-acrylamido-2-methylpropanesulfonic acid.

48.- A compound according to claim 37 having an average molecular weight between 10000 and 100000 Daltons.

49.- A compound according to claim 43 wherein R<sub>2</sub> represents -COCH<sub>3</sub>.

50.- A compound according to claim 49 having an average molecular weight of 48000 Daltons, a polydispersity index of 1.8 and <sup>1</sup>H and <sup>13</sup>C NMR spectra in accordance with the ones shown in figure 3.

51.- A compound according to claim 46 wherein R<sub>2</sub> represents -COCH<sub>3</sub>.

52.- A compound according to claim 47 wherein R<sub>2</sub> represents -COCH<sub>3</sub>.

53.- A compound according to claim 51 with a molar fraction m of about 0.2 and a molar fraction n of about 0.8, an average molecular weight of 33000 Daltons, a polydispersity index of 2.4 and <sup>1</sup>H and <sup>13</sup>C NMR spectra in accordance with the ones shown in figure 5.

54.- A compound according to claim 51 with a molar fraction m of about 0.4 and a molar fraction n of about 0.6, an average molecular weight of 34000 Daltons, a polydispersity index of 2.6 and a <sup>1</sup>H NMR spectrum in accordance with that shown in figure 8.

55.- A compound according to claim 51 with a molar fraction m of about 0.6 and a molar fraction n of about 0.4, an average molecular weight of 35000 Daltons, a polydispersity index of 2.5 and a <sup>1</sup>H NMR spectrum in accordance with that shown in figure 7.

56.- A compound according to claim 51 with a molar fraction m of about 0.8 and a molar fraction n of about 0.2, an average molecular weight of 38000 Daltons, a polydispersity index of 2.8 and a <sup>1</sup>H NMR spectrum in accordance with that shown in figure 6.

57.- A compound according to claim 52 with a molar fraction m of about 0.8 and a molar fraction n of about 0.2, an average molecular weight of 43000 Daltons, a polydispersity index of 2.5 and <sup>1</sup>H and <sup>13</sup>C NMR spectra in accordance with the ones shown in figure 10.

58.- A process for the preparation of a polymeric compound of formula I

wherein: R<sub>1</sub> represents hydrogen or C<sub>1-4</sub> alkyl;  
R<sub>2</sub> represents -COCH<sub>3</sub> or hydrogen;  
X represents -(CH<sub>2</sub>CH<sub>2</sub>O)<sub>p</sub>-; and

[illegible]

p represents an integer from 1 to 100.

64.- A compound according to claim 63 wherein R<sub>1</sub> represents methyl and p represents 1.

65.- The compound 2-(methacryloyloxy)ethyl 2-(acetyloxy)-4-(trifluoromethyl)benzoate.



REMARKS

The amendments are made to correct improper multiple dependencies and to delete improper claims. No new subject matter has been added.

Respectfully submitted,

By Barbara G. Ernst

Barbara G. Ernst  
Attorney for Applicants  
Registration No. 30,377  
ROTHWELL, FIGG, ERNST & MANBECK, p.c.  
Suite 701-E, 555 13th Street, N.W.  
Washington, D.C. 20004  
Telephone: (202)783-6040

14/pdr

10/070244  
JC13 Rec'd PCT/PTO 04 MAR 2002

New biocompatible polymeric systems carrying triflusal or HTB.

The present invention relates to a new series of biocompatible polymeric systems, and more specifically to a new series of biocompatible polymeric systems carrying triflusal or HTB. The invention also relates to a process for their preparation, as well as to their uses, particularly as coatings for prostheses and other devices that are in contact with blood during use.

Background of the invention

The use of synthetic materials in the field of cardiovascular surgery and particularly in the reconstruction of the vascular system has been one of the greatest advances in this field. The materials used must not only possess suitable physicochemical properties such as flexibility, hydrolytic stability and fatigue strength, but it is essential that they exhibit a good blood biocompatibility or hemocompatibility. The contact of the prosthetic devices with the blood flow leads to the deposition of plasmatic proteins on the surface of the material and to the activation of the coagulation cascade, generating a thrombogenic surface.

No material has yet been found that can be regarded in a strict sense as non-thrombogenic, although certain materials have been used with success in the manufacture of big-diameter ( > 6 mm) vascular prostheses. Thus, for example, during the last decades commercially available synthetic vascular grafts based mainly on meshes woven or knitted with polyester (Dacron<sup>®</sup>), polyamide (Nylon<sup>®</sup>) or polytetrafluoroethylene (PTFE, Teflon<sup>®</sup>) fibres as well as porous, expanded PTFE (Goretex<sup>®</sup>) systems have been used. Whereas this type of prostheses works relatively well when used to substitute big-diameter vessels, the failure rate at short- or mid-term is quite high when they are used to substitute small- or medium-calibre vessels due to the appearance of thrombosis. It is therefore still necessary to improve the materials used up to now for this kind of applications.

Triflusal, whose chemical name is 2-acetyloxy-4-trifluoromethylbenzoic acid, is a platelet aggregation inhibitor marketed for the treatment of thromboembolic disorders. Its main metabolite, known by the acronym HTB and whose chemical name is 2-hydroxy-4-trifluoromethylbenzoic acid, also exhibits a remarkable platelet aggregation-inhibitory activity. Both compounds are disclosed in the patent US 4,096,252.

The present invention provides a new series of biocompatible polymeric derivatives carrying triflusal or HTB, which, when used as coatings for the surface of prostheses and other devices that are in contact with blood during use, improve

Description of the invention.

$$\text{---} \left[ \text{B} \right]_n \text{---} \left[ \text{A} \right]_m \text{---}$$

5

10

and wherein the A and B units are distributed randomly in the polymer.

15

20

25

30

The present invention therefore also relates to the use of a polymeric compound of formula I as coating for non-biological materials, and particularly as coating for vascular prostheses, artificial cardiac valves and stents.

5 The invention further relates to the use of triflusal or HTB for the preparation of biocompatible polymeric compounds for coating non-biological materials, particularly vascular prostheses, artificial cardiac valves and stents.


The present invention further relates to a device or article which comprises a surface of a non-biological material that is going to be in contact with blood during use coated with a polymer carrying triflusal or HTB of formula I, and particularly to vascular prostheses, artificial cardiac valves and stents coated with a polymer carrying triflusal or HTB of formula I.

The present invention further relates to a process for preparing said devices or articles which comprises coating the desired device or article with a polymer carrying triflusal or HTB of formula I.

15 In the polymeric compounds of the present invention triflusal or HTB are linked to the rest of the polymeric system through hydrolysable covalent bonds. As mentioned above, triflusal or HTB are gradually released through the hydrolysis of said covalent bonds. Due to this, the polymeric compounds of the present invention can also be used as controlled delivery systems for triflusal or HTB and may therefore be useful for the treatment or prevention of all those diseases for which triflusal or HTB are indicated. The present invention therefore also relates to the use of a polymeric compound of formula I as a controlled delivery system for triflusal or HTB, having utility in therapy. Moreover, the present invention also relates to the use of a polymeric compound of formula I for the manufacture of a medicament for the treatment or prevention of the disorders for which triflusal or HTB are indicated and more particularly for the treatment or prevention of thromboembolic disorders. The present invention further relates to a pharmaceutical composition which comprises a polymeric compound of formula I and one or more pharmaceutically acceptable excipients. Said compositions can be prepared following conventional procedures, well known to those skilled in the art.

Throughout the present specification and particularly in formula I, the term residue of a polymerisable monomer, whether acrylic, vinylic or of a different type, shall be understood as the residue resulting from the polymerization of the

corresponding monomer. Thus, for example, when the polymerisable monomer corresponding to B is N,N-dimethylacrylamide, in formula I B represents in fact the residue of said monomer once polymerized, as shown below:




"polymerisable monomer precursor  
of B in formula I"

"B (residue of the monomer after  
polymerization)"

Unless otherwise specified, the nomenclature A and B will be used throughout the present specification to refer without distinction to the polymerisable monomer or to the corresponding polymerized residue in the polymer of formula I.

In formula I, A represents a residue of any polymerisable acrylic or vinylic monomer carrying trifusal or HTB. The expression "carrying trifusal or HTB" means that the monomer comprises a molecule of trifusal or HTB linked to the rest of the acrylic or vinylic moiety through a covalent bond that is hydrolysable *in vivo*, that is under physiological conditions. A preferred group of monomers carrying trifusal or HTB for the preparation of the polymers of formula I are those corresponding to formula II:



(II)

wherein:  $\text{R}_1$  represents hydrogen or  $\text{C}_{1-4}$  alkyl;

$R_2$  represents  $-\text{COCH}_3$  or hydrogen;  
 $X$  represents  $-(\text{CH}_2\text{CH}_2\text{O})_p-$ ; and  
 $p$  represents an integer from 1 to 100.

Within the compounds of formula II, those compounds wherein  $R_1$  represents methyl and  $p$  represents 1 are particularly preferred.

These monomers carrying triflusal or HTB, useful for the preparation of the polymers of formula I, are novel and form a further aspect of the present invention.

With regard to B, this represents a residue of a second polymerisable monomer, so that when B is present in a polymeric compound of formula I (that is, when  $n$  is different from 0) the resulting compound is a copolymer, whereas when B is absent (that is, when  $n$  is 0) the resulting compound is a homopolymer. Examples of possible meanings for B include, among others, 2-hydroxyethyl methacrylate, methyl methacrylate, methyl acrylate, N-vinylpyrrolidone, acrylic acid, methacrylic acid, acrylamide, N,N-dimethylacrylamide, vinyl acetate and 2-acrylamido-2-methylpropanesulfonic acid. Furthermore, monomer B can also be another polymerisable monomer carrying triflusal or HTB.


Although the present invention encompasses all the compounds mentioned above, a preferred group of compounds of the present invention are those polymeric compounds of formula I wherein the hydrolysable covalent bond through which triflusal or HTB are linked is a carboxylic ester bond.

Another preferred group of compounds are those compounds of formula I wherein  $n$  represents 0.

Another preferred group of compounds are those compounds of formula I wherein  $n$  is different from 0.

A more preferred group of compounds of formula I are those polymeric compounds corresponding to relative formula Ia:

6



(Ia)

wherein:  $R_1$  represents hydrogen or  $C_{1-4}$  alkyl;  
 $R_2$  represents  $-COCH_3$  or hydrogen;  
 5  $X$  represents  $-(CH_2CH_2O)_p-$ ;  
 $p$  represents an integer from 1 to 100; and  
 $B$ ,  $m$  and  $n$  have the previously described meaning.

A still more preferred group of compounds of the present invention are those compounds of formula **Ia** wherein  $R_1$  represents methyl and  $p$  represents 1.

10 A particularly preferred group of compounds are those compounds of formula **Ia** wherein  $R_1$  represents methyl;  $p$  represents 1 and  $n$  represents 0.

Another particularly preferred group of compounds are those compounds of formula **Ia** wherein  $R_1$  represents methyl;  $p$  represents 1 and  $n$  is different from 0. Within this group of compounds, those compounds wherein  $B$  represents a residue of 2-hydroxyethyl methacrylate, methyl methacrylate, methyl acrylate, N-vinylpyrrolidone, acrylic acid, methacrylic acid, acrylamide, N,N-dimethylacrylamide, vinyl acetate and 2-acrylamido-2-methylpropanesulfonic acid are preferred, and those compounds wherein  $B$  represents a residue of N,N-dimethylacrylamide or 2-acrylamido-2-methylpropanesulfonic acid are still more preferred.

20





isopropanol, hexane, heptane or diethyl ether. In general, it is advisable to use a high precipitant/solution ratio, that is of at least 10 times the volume of precipitant with regard to the volume of solution, to guarantee a good precipitation.

The acrylic or vinylic monomers carrying triflusal or HTB can be prepared in general through the formation of the covalent bond between a suitable acrylic or vinylic derivative and triflusal or HTB, or a reactive derivative thereof, following similar procedures to those described in the literature for the preparation of said type of covalent bonds.

Processes for preparing triflusal or HTB are described in the US patent mentioned above (US 4,096,252).

As stated above, the polymeric compounds of the present invention can be used as coatings for non-biological materials such as prostheses, stents and the like, improving the thrombogenic properties of said materials. Said coatings can be prepared in general by immersion of the surface to be coated in a diluted solution, for example 1-2% w/v, of the desired polymer in a suitable solvent such as dimethylformamide, ethanol, water/ethanol mixtures or dioxane/ethanol mixtures.

Brief description of the figures:

Figure 1 shows the synthesis of the monomer carrying triflusal described in example 1;

Figure 2 shows the synthesis of the polymer described in example 2;

Figure 3 shows the  $^1\text{H}$  (3A) and  $^{13}\text{C}$  (3B) NMR spectra of the polymer of example 2;

Figure 4 shows the synthesis of a poly[THEMA-co-DMA] copolymer described in example 3;

Figure 5 shows the  $^1\text{H}$  (5A) and  $^{13}\text{C}$  (5B) NMR spectra of the polymer 3A described in example 3;

Figure 6 shows the  $^1\text{H}$ -NMR spectrum of the polymer 3B described in example 3;

Figure 7 shows the  $^1\text{H}$ -NMR spectrum of the polymer 3C described in example 3;

Figure 8 shows the  $^1\text{H}$ -NMR spectrum of the polymer 3D described in example 3;

Figure 9 shows the synthesis of a poly[THEMA-co-AMPS] copolymer

described in example 4;

Figure 10 shows the  $^1\text{H}$  (10A) and  $^{13}\text{C}$  (10B) NMR spectra of the polymer described in example 4;

Figure 11 shows the release of HTB from polymer 3A in rat plasma following the method described in example 5.

The following examples are included herein to illustrate the preparation and uses of the compounds of the present invention. In any case they are to be understood as limiting the scope of the invention in any way.

In the following examples, polymers were analyzed by  $^1\text{H}$  and/or  $^{13}\text{C}$  nuclear magnetic resonance (NMR) spectroscopy in the particular conditions mentioned in each case.

The molar fractions m and n in the copolymers were determined by  $^1\text{H}$ -NMR analysis. Due to the experimental error of the technique, the values of said molar fractions may vary by up to a 5%.

The average molecular weights were determined by Gel Permeation Chromatography (GPC) using a Perkin Elmer apparatus equipped with an isocratic pump LC 250 and a refractive index detector series 200. Data were acquired with a PL-DCU (Polymer Laboratories). Samples were eluted using a set of 3 polystyrene – divinylbenzene pL-gel columns of 500,  $10^4$  and  $10^5$  Å of nominal pore size (Polymer Laboratories).

#### Example 1: Preparation of 2-(methacryloyloxy)ethyl 2-acetyloxy-4-(trifluoromethyl)benzoate (THEMA)

The preparation of this compound is shown in the scheme of Fig. 1.

##### a) 2-Acetyloxy-4-(trifluoromethyl)benzoic acid chloride

In a round-bottomed flask 0.1 mols of triflusal were reacted with 70 mL of  $\text{SOCl}_2$ , the flask was connected to a refrigerant and the reaction was heated at reflux for 4 h, under magnetic stirring. Next, the unreacted  $\text{SOCl}_2$  excess was removed by distillation, first at atmospheric pressure and then at reduced pressure. Then, the desired acid chloride was isolated by distillation at reduced pressure. The yield of the reaction was 64 %.

$^1\text{H}$ -NMR ( $\text{DMSO-d}_6$ , 300 MHz,  $20^\circ\text{C}$ );  $\delta$ : 8.1 (d, 1H, arom), 7.7 (d, 1H, arom), 7.6 (s, 1H, arom), 2.3 (s, 3H,  $\text{CH}_3\text{COO-}$ ).

In a flask were mixed 0.025 mols of 2-hydroxyethyl methacrylate (HEMA) and 5.21 mL Et<sub>3</sub>N (0.025 mols) in 100 mL of diethylether as solvent. To this mixture, 0.025 mols of the acid chloride obtained in step a) dissolved in diethyl ether was added dropwise, under nitrogen flux and at room temperature. Once the acid chloride addition was complete, the reaction was kept under stirring for 24 hours. The precipitated triethylamine hydrochloride was removed by filtration. The filtrate was washed first with water containing some drops of concentrated HCl, and then with water several times. The aqueous phase was discarded and the organic phase was dried over anhydrous MgSO<sub>4</sub>. Finally, ether was removed under vacuum until constant weight. The yield of the reaction was 52%.

<sup>1</sup>H-NMR (DMSO-d<sub>6</sub>, 300 MHz, 20°C); δ: 8.1 (d, 1H, arom), 7.8 (d, 1H, arom), 7.7 (s, 1H, arom), 6.1 and 5.7 (d, m, CH<sub>2</sub>=C<), 4.6 and 4.4 (t,t, -CH<sub>2</sub>-CH<sub>2</sub>-), 2.3 (s, 3H, CH<sub>3</sub>COO-), 1.9 (s, 3H, CH<sub>3</sub>-C=).

This compound was prepared by polymerization of the monomer carrying triflusal obtained in example 1 (THEMA). The chemical structure of this compound and its synthesis are shown in the scheme of Fig. 2.

In Pyrex glass ampoules, 5 g of THEMA (obtained in example 1) was dissolved in 28 mL of a (4:1) purified dioxane/acetone mixture, the concentration of the solution thus being 0.5M. Next, benzoyl peroxide ( $1.5 \times 10^{-2}$  M) was added as the initiator; for the solution described above 100.8 mg were used. Oxygen was then removed from the solution by bubbling nitrogen (30 min) twice.

The sealed ampoules were immersed in a thermostatic bath at 60°C for 24 h. After polymerization, the polymer was precipitated by pouring it into an excess of ethanol; to precipitate 5 g of polymer 500 mL of ethanol was used, to which the polymer solution was added dropwise. This operation was carried out in an ice bath. The solution was kept under stirring for 4 h and was then filtered under vacuum. The precipitate thus obtained was washed several times with ethanol, was filtered again, and was then dried in a high vacuum drying oven until constant weight. The yield of the reaction was 90%.

The average molecular weight of this polymer, determined by Gel Permeation Chromatography (GPC), was 48000 Daltons, with a polydispersity index  $M_w/M_n$  of 1.8.

The  $^1\text{H}$  (400 MHz,  $\text{CDCl}_3$ ,  $45^\circ\text{C}$ ) and  $^{13}\text{C}$  (100 MHz,  $\text{DMSO-d}_6$ ,  $45^\circ\text{C}$ ) NMR spectra of the polymeric compound obtained in this example are shown in Fig. 3 (A and B).

Example 3: Preparation of copolymers from THEMA and N,N-dimethylacrylamide (DMA) having various m/n molar fractions (poly[THEMA-co-DMA])

The chemical structure of these copolymers and their synthesis are shown in the scheme of Fig. 4.

The preparation of a representative THEMA-DMA copolymer is carried out as follows:

1 g of THEMA (obtained in example 1) and 1 g of DMA was dissolved in 25.75 mL of purified dioxane, the final concentration of the solution being 0.5 M. Next, 46.75 mg of benzoyl peroxide at a concentration of  $1.5 \times 10^{-2}$  M was added and oxygen was removed from the solution by bubbling nitrogen twice for 30 minutes.

The sealed ampoule was immersed in a thermostatic bath at  $60^\circ\text{C}$  for 24 h. The polymer was then precipitated by pouring the resulting solution dropwise into 1 L of diethyl ether. The solution was kept under stirring for 4 h, diethyl ether was then removed by decantation and the precipitate was dried under vacuum until constant weight. The yield of the reaction was 80%.

$^1\text{H}$ -NMR analysis showed that this copolymer (designated from now on polymer 3A) contains a 52 wt % of THEMA with a m/n molar fraction of 0.18/0.82. GPC determination showed that the average molecular weight was 33000 Daltons, with a polydispersity index of 2.4.

$^1\text{H}$  (200 MHz,  $\text{CDCl}_3$ ,  $40^\circ\text{C}$ ) and  $^{13}\text{C}$  (100 MHz,  $\text{CDCl}_3$ ,  $45^\circ\text{C}$ ) NMR spectra of polymer 3A are shown in Fig. 5 (A and B).

Preparation of other copolymers from THEMA and N,N-dimethylacrylamide (DMA) (poly[THEMA-co-DMA]): Following an analogous procedure to that described to prepare polymer 3A, but changing the proportions of the two monomers (THEMA and DMA) as mentioned below, the following copolymers were obtained:

- 1) Poly[THEMA-co-DMA] with a molar fraction of 0.20 of DMA in the monomer feed (polymer 3B):

0.13 g of DMA and 1.87 g of THEMA was dissolved in 13 mL of purified dioxane (0.5M). Then, 47.2 mg of benzoyl peroxide at a concentration of  $1.5 \times 10^{-2}$  M was added. The experimental conditions for the polymerization and isolation are the same as mentioned above for polymer 3A.

Yield of the polymerization (percentage conversion in weight): 85 %.

Molar fraction m/n = 0.79/0.21

Molecular weight  $M_n$  = 38000 Dalton

Polydispersity index  $M_w/M_n$  = 2.8

$^1\text{H-NMR}$  spectrum (200 MHz,  $\text{CDCl}_3$ ,  $40^\circ\text{C}$ ): shown in Figure 6.

- 2) Poly[THEMA-co-DMA] with a molar fraction of 0.40 of DMA in the monomer feed (polymer 3C):

0.31 g of DMA and 1.69 g of THEMA was dissolved in 15.65 mL of purified dioxane (0.5M). Then, 56.81 mg of benzoyl peroxide at a concentration of  $1.5 \times 10^{-2}$  M was added. The experimental conditions for the polymerization and isolation are the same as mentioned above for polymer 3A.

Yield of the polymerization (percentage conversion in weight): 91.5 %

Molar fraction m/n = 0.61/0.39

Molecular weight  $M_n$  = 35000 Dalton

Polydispersity index  $M_w/M_n$  = 2.5

$^1\text{H-NMR}$  spectrum (200 MHz,  $\text{CDCl}_3$ ,  $40^\circ\text{C}$ ): shown in Figure 7.

- 3) Poly[THEMA-co-DMA] with a molar fraction of 0.60 of DMA in the monomer feed (polymer 3D):

0.58 g of DMA and 1.42 g of THEMA was dissolved in 19.7 mL of purified dioxane (0.5M). Then, 95.98 mg of benzoyl peroxide at a concentration of  $1.5 \times 10^{-2}$  M was added. The experimental conditions for the polymerization and isolation are the same as mentioned above for polymer 3A.

Yield of the polymerization (percentage conversion in weight): 89 %

Molar fraction m/n = 0.42/0.58

Molecular weight  $M_n = 34000$  Dalton

Polydispersity index  $M_w/M_n = 2.6$

$^1\text{H}$ -NMR spectrum (200 MHz,  $\text{CDCl}_3$ ,  $40^\circ\text{C}$ ): shown in Figure 8.

5 Example 4: Preparation of a copolymer from THEMA and 2-acrylamido-2-methylpropanesulfonic acid (AMPS) (poly[THEMA-co-AMPS])

The chemical structure of this polymer and its preparation are shown in the scheme of Figure 9.

10 To prepare this polymer, 1 g of THEMA (obtained in example 1) and 0.144 g of AMPS was dissolved in 12 mL of (9:1) purified dioxane/water in a Pyrex glass ampoule, the concentration of the solution being 0.25 M. As polymerization initiator, 2,2-azobisisobutyronitrile (AIBN) at a concentration of  $1.5 \times 10^{-2}$  M was used, in this case we used 59.1 mg. Next,  $\text{N}_2$  was bubbled through the solution to  
15 remove oxygen from the system, twice for 30 minutes.

The sealed flask was immersed in a thermostatic bath at  $50^\circ\text{C}$  for 24 h. The solvent was then partly removed using a rotary evaporator and the polymer was then precipitated with 100 mL of diethyl ether. The solution was kept under stirring for 1 h and the solvent was then removed using a rotary evaporator. The  
20 residue was dissolved in 10 mL of distilled water and was then freeze-dried. The yield of the process was 100 %.

To purify the polymer, 500 mg of the copolymer obtained was dissolved in 10 mL of chloroform and the copolymer was precipitated by pouring this solution over 100 mL of diethyl ether dropwise, under stirring for 4 h. The polymer was  
25 then isolated by filtration under vacuum and was dried until constant weight.

$^1\text{H}$ -NMR analysis showed that the copolymer has a m/n molar fraction of 0.77 in THEMA and 0.23 in AMPS.

The average molecular weight of this polymer, determined by GPC, was 43000 Dalton, with a polydispersity index of 2.5.

30  $^1\text{H}$  (200 MHz,  $\text{DMSO}-d_6$ ,  $40^\circ\text{C}$ ) and  $^{13}\text{C}$  (300 MHz,  $\text{DMSO}-d_6$ ,  $40^\circ\text{C}$ ) NMR spectra of the copolymer described in this example are shown in figure 10 (A and B).

Example 5: Study of the release of the antiaggregating compound contained in a polymer of formula I in rat plasma

The release of the antiaggregating agent from the polymers of the present invention can be assessed using an *in vitro* assay comprising the incubation at 37° C and under constant stirring of rat plasma to which a solution of the desired polymer has been added and then determine at different times the release of the drug by HPLC. In parallel, and in order to check the linearity and accuracy of the method, the same assay was performed using stock solutions of the drug.

a) Plasma preparation

Rat plasma was obtained by cardiac puncture. Animals were placed in a chamber previously saturated with diethyl ether; when animals were anesthetized, they were placed in ventral position and were fastened to a table in order to carry out a cardiac puncture through the intercostal space. Blood was transferred to polypropylene tubes containing 20% of 3.2% sodium citrate as anticoagulant, tubes were closed and homogenized manually. Plasma was obtained by blood centrifugation at 2000 g.

b) Solution preparation

For this assay, the polymer 3A obtained in example 3 was used. This polymer carries triflusal. In this case, due to the well-known hydrolysis of triflusal in aqueous media to give its metabolite, HTB, the release of HTB was followed by HPLC.

The powdered polymer was dissolved in methanol and solutions having a concentration of 0.96 mg/mL, equivalent to a total HTB concentration of 1.4 mM, were prepared. In parallel, the same assay was performed using HTB stock solutions in order to obtain a suitable calibration curve. The concentrations of HTB used were: 1.25 mM, 1.5 mM, 6.2 mM and 9.3 mM.

c) Release assay

The rat plasma prepared as described in step a) was divided into 0.2 mL volumes which were distributed in polypropylene tubes. To each tube, 10 µL of the polymer solution was added. Tubes were immersed in a bath at 37 °C under constant stirring. Aliquotes were collected at different times and were analyzed by HPLC, using the following conditions:

- Waters µBoundapak C-18 column of 3.9x300 mm;
- Perkin Elmer LC-250 pump;
- UV/Vis detector Perkin-Elmer LC-95;  $\lambda$  = 305 nm.
- Waters 770 Data Module integrator

Before HPLC analysis, samples were prepared by precipitating plasmatic proteins with methanol 1:5, followed by centrifugation at 15000 rpm for 10 min.

#### d) Results

10

Commercial Goretex® vascular grafts were immersed into a 1:1 dioxane/ethanol solution of the polymer of example 2 (2 wt %) for 30 min. The wet segments of the prostheses were dried at room temperature in a controlled atmosphere of nitrogen until constant weight. The thickness and quantity of the coating was determined by measuring the weight gain of the coated prostheses with respect to the original uncoated prostheses. Homogeneous coatings having a thickness of about 3-5 µm were obtained.

Similar results were obtained using polymer 3A obtained in example 3.

The effect of the application of a polymer of the invention as coating of a non-biological material upon the thrombogenic properties of the latter can be evaluated *in vitro* by measuring the platelet aggregation on a material coated with a polymer of the invention in comparison to that observed in the uncoated material; platelet aggregation can be monitored by determining the amount of platelets retained on the material or by scanning electron microscopy (SEM).

For this study, platelet-rich plasma (PRP) from sheep arterial blood was used. PRP was isolated by centrifugation of 40 mL blood at 1500 rpm for 10 min.



After this time, the supernatant was discarded and the content of platelets was determined with a hematologic counter Serono-3000. The non-biological material used in this assay were Goretex<sup>®</sup> vascular grafts of 4 mm inner diameter. A group of prostheses coated with a polymer and a control group (uncoated prostheses) were used.

Prostheses were mounted on seeding chambers and 100  $\mu$ L of PRP was added. Chambers were incubated at 37 °C in an incubator (5% CO<sub>2</sub>) during different periods of time. After the assay time, prostheses were washed three times with MEM (Minimal Essential Medium) to remove non-retained platelets and the number of platelets retained in the prostheses in comparison with the control group was determined indirectly by counting the number of platelets recovered at each of the assay times.

After this, samples were fixed with glutaraldehyde, washed with buffered solution (pH 7.4), dehydrated in a graded acetone series and metallized with gold/palladium for their examination by SEM using a scanning electron microscope Zeiss 950 DSM.


#### b) Results

Using this assay, it has been observed that the coating of Goretex<sup>®</sup> prostheses with a thin layer of the polymer obtained in example 2 following the method disclosed in example 6 decreases the retention of platelets in comparison with the uncoated prostheses. In addition, the analysis by SEM shows that platelets are less aggregated in the case of coated prostheses, while the uncoated prostheses (control group) present coagulated domains of aggregated platelets with a strong adhesion to the porous structure of the surface of Goretex<sup>®</sup>.

These results show the utility of the polymers of the invention to improve the thrombogenic properties of non-biological materials that are in contact with the blood during use.

## CLAIMS

1.- A polymeric compound of relative general formula I



(I)

wherein:

A represents a residue of a polymerisable acrylic or vinylic monomer carrying triflusal or HTB, wherein triflusal or HTB are linked to the remainder of the monomer molecule through an *in vivo* hydrolysable covalent bond;

B represents a residue of a second polymerisable monomer;

m and n represent the molar fractions of the monomers A and B in the polymer so that m + n is always 1 and m is always different from 0;


and wherein the A and B units are distributed randomly in the polymer.

2.- A compound according to claim 1 wherein the hydrolysable covalent bond through which triflusal or HTB are linked is a carboxylic ester bond.

3.- A compound according to claim 1 wherein n represents 0.

4.- A compound according to claim 1 wherein n is different from 0.

5.- A compound according to claim 1 of relative formula Ia:



(Ia)

wherein:  $R_1$  represents hydrogen or  $C_{1-4}$  alkyl;  
 $R_2$  represents  $-COCH_3$  or hydrogen;  
 $X$  represents  $-(CH_2CH_2O)_p-$ ;  
 $p$  represents an integer from 1 to 100; and  
 $B$ ,  $m$  and  $n$  have the meaning described in claim 1.

6.- A compound according to claim 5 wherein  $R_1$  represents methyl and  $p$  represents 1.

7.- A compound according to claim 6 wherein  $n$  represents 0.

8.- A compound according to claim 6 wherein  $n$  is different from 0.

9.- A compound according to claim 8 wherein  $B$  represents a residue of 2-hydroxyethyl methacrylate, methyl methacrylate, methyl acrylate, N-vinylpyrrolidone, acrylic acid, methacrylic acid, acrylamide, N,N-dimethylacrylamide, vinyl acetate or 2-acrylamido-2-methylpropanesulfonic acid.

10.- A compound according to claim 9 wherein  $B$  represents a residue of N,N-dimethylacrylamide.

11.- A compound according to claim 9 wherein  $B$  represents a residue of 2-acrylamido-2-methylpropanesulfonic acid.

12.- A compound according to any of the preceding claims having an average

molecular weight between 10000 and 100000 Daltons.

13.- A compound according to claim 7 wherein  $R_2$  represents  $-\text{COCH}_3$ .

14.- A compound according to claim 13 having an average molecular weight of 48000 Daltons, a polydispersity index of 1.8 and  $^1\text{H}$  and  $^{13}\text{C}$  NMR spectra in accordance with the ones shown in figure 3.

15.- A compound according to claim 10 wherein  $R_2$  represents  $-\text{COCH}_3$ .

16.- A compound according to claim 11 wherein  $R_2$  represents  $-\text{COCH}_3$ .

17.- A compound according to claim 15 with a molar fraction m of about 0.2 and a molar fraction n of about 0.8, an average molecular weight of 33000 Daltons, a polydispersity index of 2.4 and  $^1\text{H}$  and  $^{13}\text{C}$  NMR spectra in accordance with the ones shown in figure 5.

18.- A compound according to claim 15 with a molar fraction m of about 0.4 and a molar fraction n of about 0.6, an average molecular weight of 34000 Daltons, a polydispersity index of 2.6 and a  $^1\text{H}$  NMR spectrum in accordance with that shown in figure 8.

19.- A compound according to claim 15 with a molar fraction m of about 0.6 and a molar fraction n of about 0.4, an average molecular weight of 35000 Daltons, a polydispersity index of 2.5 and a  $^1\text{H}$  NMR spectrum in accordance with that shown in figure 7.

20.- A compound according to claim 15 with a molar fraction m of about 0.8 and a molar fraction n of about 0.2, an average molecular weight of 38000 Daltons, a polydispersity index of 2.8 and a  $^1\text{H}$  NMR spectrum in accordance with that shown in figure 6.

21.- A compound according to claim 16 with a molar fraction m of about 0.8 and a molar fraction n of about 0.2, an average molecular weight of 43000 Daltons, a polydispersity index of 2.5 and  $^1\text{H}$  and  $^{13}\text{C}$  NMR spectra in accordance with the ones shown in figure 10.

22.- A process for the preparation of a polymeric compound of formula I according to claim 1 which comprises the radical polymerization of a monomer A and optionally a second monomer B in the molar fractions m and n, respectively, wherein A, B, m and n have the meaning described in claim 1, in the presence of a polymerization initiator, in a suitable solvent.

23.- Use of a polymeric compound of formula I according to any of claims 1 to 21 as coating for non-biological materials.

25.- Use of triflusal or HTB for the preparation of biocompatible polymeric compounds for coating non-biological materials.


27.- A device or article which comprises a surface of a non-biological material that is going to be in contact with blood during use coated with a polymer carrying triflusal or HTB of formula I according to any of claims 1 to 21.

29.- Process for preparing a device or article according to claim 27 or 28 which comprises coating said device or article with a polymer carrying triflusal or HTB of formula I according to any of claims 1 to 21.

31.- Use of a polymeric compound of formula I according to any of claims 1 to 21 for the manufacture of a medicament for the treatment or prevention of the disorders for which triflusal or HTB are indicated.

33.- A pharmaceutical composition which comprises a polymeric compound of formula I according to any of claims 1 to 21 and one or more pharmaceutically acceptable excipients.

34.- A compound of formula II



(II)

wherein: R<sub>1</sub> represents hydrogen or C<sub>1-4</sub> alkyl;  
 5 R<sub>2</sub> represents -COCH<sub>3</sub> or hydrogen;  
 X represents -(CH<sub>2</sub>CH<sub>2</sub>O)<sub>p</sub>; and  
 p represents an integer from 1 to 100.

35.- A compound according to claim 34 wherein R<sub>1</sub> represents methyl and p represents 1.


10 36.- The compound 2-(methacryloyloxy)ethyl 2-(acetyloxy)-4-(trifluoromethyl)benzoate.

## Abstract

New biocompatible polymeric systems carrying triflusal or HTB are described which result from the polymerization of a monomer A of the acrylic or vinylic type and carrying triflusal or HTB, wherein triflusal or HTB are linked to the remainder  
 5 of the molecule of said monomer through an *in vivo* hydrolysable covalent bond, and optionally a second polymerisable monomer B. These new polymeric systems are useful as coating for synthetic biomaterials.

1/14




Fig. 1





2/14


Fig. 2



poly[THEMA]


3/14

Fig. 3A




4/14

Fig. 3B




5/14

Fig. 4




6/14

Fig. 5A




7/14

Fig. 5B




8/14

Fig. 6



9/14


Fig. 7






10/14

Fig. 8




11/14

Fig. 9



12/14

Fig. 10A



13/14

Fig. 10B





Fig. 11



<b>DECLARATION AND POWER OF ATTORNEY FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63)</b>		Attorney Docket No.	1604-130
		First Named Inventor	Alberto Gallardo Ruiz
		COMPLETE IF KNOWN	
		Application Number	Unassigned
		Filing Date	March 4, 2002
		Group Art Unit	Unassigned
		Examiner Name	Unassigned
Declaration Submitted with Initial Filing	Declaration Submitted after Initial Filing		

As a below named inventor, I hereby declare that.

My residence, mailing address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled: **NEW BIOCOMPATIBLE POLYMERIC SYSTEMS CARRYING TRIFLUSAL OR HTB** the specification of which was filed on September 1, 2000 as PCT International Application Number PCT/ES00/00335.

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Numbers	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
P9902013	ES	09/03/1999			

I hereby claim the benefit under 35 U.S.C. 119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)

I or we hereby appoint the registered practitioner(s) associated with Customer No. **6449** to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith. Direct all correspondence to Customer Number **6449**.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Received at: 7:40AM, 6/3/2002

10070244.060602




03/06/2002 12:42

33553/302

J ISERN

PAG. 03

445070101

<b>NAME OF SOLE OR FIRST INVENTOR:</b>		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any]) <u>Alberto</u>		Family Name or Surname <u>Gallardo Ruiz</u>	
Inventor's Signature 		Date <u>30/04/2002</u>	
Residence: City <u>Madrid</u>		Country <u>SPAIN ESX</u> Citizenship <u>SPAIN</u>	
Mailing Address <u>Paseo de la Castellana, 127</u>			
Mailing Address			
City <u>Madrid</u>		Postal Code <u>28046</u>	Country <u>SPAIN</u>
<b>NAME OF SECOND INVENTOR:</b>		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any]) <u>Gema</u>		Family Name or Surname <u>Rodríguez Crespo</u>	
Inventor's Signature 		Date <u>30/04/02</u>	
Residence: City <u>Madrid</u>		Country <u>SPAIN ESX</u> Citizenship <u>SPAIN</u>	
Mailing Address <u>Virgen del Sagrario, 25</u>			
Mailing Address			
City <u>Madrid</u>		Postal Code <u>28027</u>	Country <u>SPAIN</u>
<b>NAME OF THIRD INVENTOR:</b>		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any]) <u>Julio</u>		Family Name or Surname <u>San Román del Barrio</u>	
Inventor's Signature 		Date <u>30/04/02</u>	
Residence: City <u>Las Matas</u>		Country <u>SPAIN ESX</u> Citizenship <u>SPAIN</u>	
Mailing Address <u>San Lorenzo del Escorial, 38</u>			
Mailing Address			
City <u>Las Matas</u>		Postal Code <u>28290</u>	Country <u>SPAIN</u>